



equalseal.com

PO Box #13665


Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

## Buna-N-60 Durometer

Black Buna-N (Nitrile) rubber gaskets are recommended for service to resist many hydrocarbons, fats, oils, greases, hydraulic fluids and chemicals.



Buna-N-60 Durometer	Physical Properties
Color	Black
Durometer Shore A	60 +/-5
Service Temperature	-40 to 250 ° F
Tensile Strength	900 psi
Ultimate Elongation	200 %
Weight (per sq. ft. 1/8 thick)	0.9 Lb.
SAE J200 Call Out	SAE J200 1BF 609