



equalseal.com
PO Box #13665
Fairlawn OH 44334
Phone: (330) 984-0747
Fax: (330) 752-4119

SCE-42

These rolls are a blend of Neoprene, EPDM and SBR. It is very compressible and flexible.



| SCE-42 | Physical Properties |
|---|---------------------|
| Color | Black |
| Density ASTM D1056 | 4 to 8 Lb/Ft3 |
| Service Temperature | -40 to 185 ° F |
| Compression Deflection 25% (ASTM D1056) | 5 to 9 psi |
| Compression Set Max (ASTM D1056) | 40 % |
| Water Absorption Max (ASTM D1056) | 10 % |
| Tensile Strength ASTM D412 (DIE A) | 75 psi |
| Ultimate Elongation ASTM D412 (DIE A) | 125 % |
| CD Change After Oven Aging ASTM D1056 | +/- 30 % |