



equalseal.com

PO Box #13665

Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

## SCE-42

These rolls are a blend of Neoprene, EPDM and SBR. It is very compressible and flexible.



SCE-42	Physical Properties
Color	Black
Density ASTM D1056	4 to 8 Lb/Ft3
Service Temperature	-40 to 185 ° F
Compression Deflection 25% (ASTM D1056)	5 to 9 psi
Compression Set Max (ASTM D1056)	40 %
Water Absorption Max (ASTM D1056)	10 %
Tensile Strength ASTM D412 (DIE A)	75 psi
Ultimate Elongation ASTM D412 (DIE A)	125 %
CD Change After Oven Aging ASTM D1056	+/- 30 %