



equalseal.com

PO Box #13665


Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

EPDM - White FDA Grade

Great for outdoor environments. Offers excellent resistance to ozone, oxidants, and severe weather conditions. FDA approved ingredients per 21CFR 177.260.



EPDM - White FDA Grade

Physical Properties

Color	Off White
Durometer Shore A	60
Service Temperature	-40 to 200 ° F
Ultimate Elongation	300 %
Tensile Strength	1000 psi
FDA Approved	21 CFR 177.2600