



equalseal.com

PO Box #13665

Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

## EPDM - 60 Durometer

EPDM (ethylene propylene diene monomer) rubber is recommended for service to resist animal and vegetable oils, ozone, strong and oxidizing chemicals.



EPDM - 60 Durometer	Physical Properties
Color	Black
Durometer Shore A	60
Service Temperature	-40 to 212 ° F
Tensile Strength	800 psi
Ultimate Elongation	250 %
Weight (per sq. ft. 1/8 thick)	0.86 Lb.
ASTM D2000 Line Call Out	ASTM D2000 3BA608C12
Mil Spec Call Out	MIL R-3065 RS 608 C1
SAE J200 Call Out	SAE J200 3BA 608 C12