



equalseal.com

PO Box #13665

Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

Equalseal EQ750W

Equalseal EQ 750W is a high quality general service sheet, with synthetic fibers and an NBR binder. Recommended for use in sealing against oils, solvents, fuels, non-aggressive solutions, and service conditions up to 750 F.



| Equalseal EQ750W | Physical Properties |
|--|------------------------|
| Color | Off-White |
| Composition | Aramid/NBR |
| Density | 109 lb/ft ³ |
| Service Temperature | -100 to 750 ° F |
| Service Pressure | 0 to 1380 psi |
| Compressibility (after 1 hour at 210° F) - ASTM F36/J | 7 to 17 % |
| Recovery ASTM F36A Minimum (%) | 45 % |
| Creep Relaxation 7250 psi / 572 F | 25 % |
| Thickness Increase (max%) ASTM F146 (ASTM Oil Fuel B) | 15 % |
| Thickness Increase (max%) ASTM F146 (Oil IRM 903, 5Hr, 302°F) | 12 % |
| Weight Increase (max%) ASTM F146 (ASTM Oil Fuel B, 5hrs, 70°F) | 15 % |
| ASTM F104 Line Call Out | F712120E22M5 |