



equalseal.com

PO Box #13665

Fairlawn OH 44334

Phone: (330) 984-0747

Fax: (330) 752-4119

Equalseal EQ750W

Equalseal EQ 750W is a high quality general service sheet, with synthetic fibers and an NBR binder. Recommended for use in sealing against oils, solvents, fuels, non-aggressive solutions, and service conditions up to 750 F.



 **equalseal EQ 750W**
aramid fiber & nbr gasket

Equalseal EQ750W	Physical Properties
Color	Off-White
Composition	Aramid/NBR
Density	109 lb/ft ³
Service Temperature	-100 to 750 ° F
Service Pressure	0 to 1380 psi
Compressibility (after 1 hour at 210° F) - ASTM F36/J	7 to 17 %
Recovery ASTM F36A Minimum (%)	45 %
Creep Relaxation 7250 psi / 572 F	25 %
Thickness Increase (max%) ASTM F146 (ASTM Oil Fuel B)	15 %
Thickness Increase (max%) ASTM F146 (Oil IRM 903, 5Hr, 302°F)	12 %
Weight Increase (max%) ASTM F146 (ASTM Oil Fuel B, 5hrs, 70°F)	15 %
ASTM F104 Line Call Out	F712120E22M5