



equalseal.com
PO Box #13665
Fairlawn OH 44334
Phone: (330) 984-0747
Fax: (330) 752-4119

EPDM NSF 61 - 75 Duro Sheet

Equalseal.com EPDM NSF-61 is a smooth finish, 75 Durometer, sulfur cured EPDM rubber sheet that has been tested and certified to meet the qualifications of NSF-61 for use in products that come in contact with potable water.



EPDM NSF 61 - 75 Duro Sheet	Physical Properties
Color	Black
Durometer Hardness Shore A ISO 868	75 +/-5
Service Temperature Limits (F)	-20 to 250 ° F
Tensile Strength (psi) ASTM D412	1500 psi
Ultimate Elongation (%) ASTM D412	150 %
Compression Set ASTM (%) D395 B	20 %
ASTM D2000 Line Call Out	3BA715A14B13C12ZA-75
Dialectric Strength ASTM D149	V/mil