



equalseal.com
PO Box #13665
Fairlawn OH 44334
Phone: (330) 984-0747
Fax: (330) 752-4119

EPDM NSF 61 - 75 Duro Sheet

Equalseal.com EPDM NSF-61 is a smooth finish, 75 Durometer, sulfur cured EPDM rubber sheet that has been tested and certified to meet the qualifications of NSF-61 for use in products that come in contact with potable water.



| EPDM NSF 61 - 75 Duro Sheet | Physical Properties |
|------------------------------------|----------------------|
| Color | Black |
| Durometer Hardness Shore A ISO 868 | 75 +/-5 |
| Service Temperature Limits (F) | -20 to 250 ° F |
| Tensile Strength (psi) ASTM D412 | 1500 psi |
| Ultimate Elongation (%) ASTM D412 | 150 % |
| Compression Set ASTM (%) D395 B | 20 % |
| ASTM D2000 Line Call Out | 3BA715A14B13C12ZA-75 |
| Dialectric Strength ASTM D149 | V/mil |