


## equalseal.com

PO Box #13665 Fairlawn OH 44334 Phone: (330) 984-0747

Fax: (330) 752-4119

## Garlock Multiswell 3760-U

The MULTI-SWELL™ 3760 is the ultimate problem solver for those lightweight flange and covers where nuisance oil and water leaks plague most industrial facilities. Unlike traditional vegetable fiber and cork gaskets that allow water and oil to wick through the body of the gasket, the MULTI-SWELL absorbs the media at the inside edge, swells, and creates a tighter, long term seal.



Bin

Garlock Multiswell 3760-U	Physical Properties
Color	Blue/Off White
Composition	Aramid Fiber andProprietary Blen
Service Temperature	-100 to 700 ° F
Service Temperature Recommended Maximum Continuous	400 ° F
Service Pressure	500 psi
Compressibility ASTM F36J (1 hr. at 210° F)	15 to 30 %
Recovery ASTM F36A	40 % min
Density	85 lbs/cu. ft.
Dialectic Strength 1/8" Thickness - ASTM D149 (3 hrs at 250° F:)	385 volts/mil
Tensile Strength ASTM F152	1000 psi
ASTM F104 Line Callout	F719909B6M3